

# iD INSPIRATION CLICK

## TECHNICAL DATA

CERTIFICATION & CLASSIFICATION	STANDARDS	iD Inspiration Click
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 33 Industrial: 42
TECHNICAL CHARACTERISTICS	STANDARDS	iD Inspiration Click
Total thickness	EN ISO 24346	4,5 mm
Wear layer thickness	EN ISO 24340	0,55
Total weight	EN ISO 23997	8000 g/m <sup>2</sup>
Wear layer binder content	EN ISO 10582	Type I
Dimensions	EN ISO 24342	Planks 19,05 x 121,10 cm, 7 planks/box = 1,61 m <sup>2</sup> 24,05 x 149,10 cm, 5 planks/box = 1,79 m <sup>2</sup> Tiles 32,38 x 60,10 cm, 9 tiles/box = 1,75 m <sup>2</sup> 49,05 x 99,10 cm, 3 tiles/box = 1,46 m <sup>2</sup>
Surface treatment (PUR)		Yes - TopCleanXP™
Bevelled edges		Yes
TECHNICAL PERFORMANCES	STANDARDS	iD Inspiration Click
Dimensional stability	EN ISO 23999	≤ 0,10 %
Curl resultant to heat	EN ISO 23999	≤ 2 mm
Reaction to fire	EN 13501-1	B <sub>f</sub> -s1 loose laid over concrete substrate
Residual indentation	EN ISO 24343-1	≤ 0,10 mm
Furniture leg	EN 424	No damage
Castor chair	ISO 4918 - EN 425	No damage
Impact sound reduction	EN ISO 717-2	ΔL <sub>w</sub> = 3 dB
Reduction of in-room impact noise	EN ISO 31-074	Class C (L <sub>n,r,w</sub> < 85 dB)
Thermal resistance	EN ISO 10456	0,04 m <sup>2</sup> K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6
Chemical resistance	EN ISO 26987	Not affected (0)
Slip resistance	DIN 51130 EN 13893	R9 / R10 depending on embossing μ ≥ 0,30
Electrical properties	EN 1815 EN 1081	< 2 kV on concrete ≥ 10 <sup>9</sup> Ohm
Peeling resistance	EN ISO 24345	≥ 50N / 50mm
Underfloor heating		Suitable - max. 27 °C


Technical data in force upon the date of publication (07/16).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

CUSTOMS TARIFF : 482050000000F



### Logistics Information



### Surface treatment



### General Information



According to European Classification ISO 10874 - EN 685

